



PATENT ABSTRACTS OF JAPAN

(11)Publication number : **63-172795**

(43)Date of publication of application : **16.07.1988**

(51)Int.Cl.

C10M163/00
//(C10M163/00
C10M125:26
C10M159:12)
C10N 30:06
C10N 30:08
C10N 40:02
C10N 50:10

(21)Application number : **62-002994**

(71)Applicant : **AMUNI KK**

(22)Date of filing : **09.01.1987**

(72)Inventor : **KUDO SHINJI**

(54) LUBRICANT

(57)Abstract:

PURPOSE: To provide a lubricating oil which is excellent in heat resistance and lubricating properties under high-temp. and heavy-load conditions and free from generation of a toxic gas and which comprises a grease and, dispersed therein, powders of an arom. resin and a hexagonal BN.

CONSTITUTION: Dispersed in a grease (A) are 0.001W5wt.% powder (B) of an arom. resin having a particle diameter up to 10 μ m selected from among a polyphenylene sulfide, a polycarbonate, a polysulfone, a polyether imide, a polyether ketone, a polyether ketone, a polyether sulfone, a polyacrylate, a polyallyl ether and a polyallyl sulfide and 0.0001W5wt.% hexagonal BN (C) having a particle size up to 1 μ m.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

BEST AVAILABLE COPY

特開昭

